

Specification Sheet for: **Reinforced Clear Vinyl**

<u>Test</u>	<u>Test Method</u>	<u>Minimum Requirement</u>
Adhesion:	5970	20
Tear:	5134	Warp: 30 Fill: 30
Flame Retardance:	5903	2.0 sec-6.0" Char
4" Tensile:	5100	Warp: 140 Fill: 125
1" before Abrasion Tensile:	5102	Warp: 85 Fill: 75
1" after Abrasion Tensile:	5304	Warp: 60 Fill: 60
Cold Temperature Resistance	5874	-40
Weight (oz/yd ²)	5041	12.0-14.0
Hydrostatic (psi)	5512	200
Width:		+1/4"-1/8"

METHODS NUMBERS REFER TO FEDERAL STANDARD #191-A TEXTILE TEST METHODS.