

Description

0.014 x 54 Anti-Static Double Clear UV, FR w/ Print
 Weight: 13.5 +/- 1.0z/yd²
 Width: 54" +/- 0.25"
 Emboss: Polish

Mechanical Properties

	Typical Values	
	WARP	FILL
TENSILE STRENGTH (5100)	100+/- 1.5 lb/in	100+/- 15 lb/in
TONGUE TEAR (5134)	5 +/- 2 lb	5 +/- 2 lb
HYDROSTATIC RESISTANCE (5512)	100 +/- 10 psi	
ELONGATION AT BREAK	>300%	
FLAME RESISTANCE (5903)		
AFTER FLAME (sec)	≤ 2.0	≤ 2.0
CHAR LENGTH (inches)	≤ 4.5	≤ 4.5
MVSS 302	Pass	
NFPA 701 METHOD	Pass	

Other Properties

HEAT SEALABLE COLD CRACK	ASTM D 136 - 20°F
UV RESISTANT	SAE-J 2527 to pass a minimum of 500 Hours exposure with a Delta E of less than 0.5 Macadam units
ANTI-STATIC	Print Grid - 10 ⁵ - 10 ⁶ OHMs PVC - 10 ⁹ - 10 ¹⁰ OHMs

Disclaimer: Above values are average values, as tested in a laboratory. All productions are subject to variations. This information above is not intended for use as strict specifications. All data obtained in the laboratory is considered accurate, however no warranty is expressed or implied.